


MOMENTO® CLEAR COAT (MATT)
Updated Apr'26


Momento® Clear Coat (Matt) is water-based Silicone-acrylic clear coat. It is specially formulated as an extra protection coating for Nippon Paint Momento® Series, special effects coating to improve washability and protects against dirt and water staining.

Product Features:

- Excellent washability
- Good adhesion on Momento® series
- Environmentally friendly
- Protects against dirt and water staining

| Paint Type | Product Type | Finishing | Recommended Substrate | Pack Size |
|-------------|---------------------|-------------------------|---------------------------|------------------------------|
| Water based | Interior & Exterior | Translucent matt finish | On top of Momento® Series | 1 Litre, 5 Litres, 18 Litres |

Composition

| | |
|---------|----------------------------|
| Pigment | : Not applicable |
| Binder | : Silicon Acrylic Emulsion |
| Thinner | : Water |

Technical Data

| | |
|----------------------|---|
| Drying Time | : Touch Dry : 1 hour (Dependent on temperature and humidity) |
| | : Hard Dry : 4 hours (Dependent on temperature and humidity) |
| Recoating Time | : minimum 2 hours (Dependent on temperature and humidity) |
| Dry Film Thickness | : Around 0.02mm per coat (based on substrate condition) |
| No. of Coats | : 2 coats |
| Theoretical Coverage | : 15-18 m ² per litre per coat (Actual coverage is dependent on substrate condition, application method, application condition and finishing appearance) |
| | <i>It is recommended to go for actual application to estimate the practical coverage for project.</i> |
| Solid Content | : Not applicable |
| Shelf Life | : Up to 36 months in tight sealed container |

Application Method

| | |
|----------------|------------------------------|
| Roller / Brush | : Dilute with 5% water |
| Spray | : Dilute with 20 – 25% water |

Recommended Coating System

Recommended on top of the below Momento® series:

- Momento® Cemento
- Momento® Coral Rock
- Momento® Snow Flake
- Momento® Stone Art Express
- Momento® Classic Tile
- Momento® Royal Stone

Surface Preparation

Remove all loose, defective paint or powdery residues, loose chalk, dust and foreign matter. Repair cracks, uneven surfaces with EasySKIM 5000 All Purpose Joint Compound or suitable fillers. Smoothen the putty / filler areas with sand paper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of the walls

This Technical Data Sheet (TDS) replaces all earlier versions.

For details or to find your nearest Nippon Paint office, visit nipponpaint.com.my

are still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the walls to be below pH9.) Spot prime with Nippon Interior Wall Sealer.

Cleaning

Clean up equipment with water immediately after use.

Safety Precautions

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness}} \right] = \text{m}^2/\text{lit}/\text{coat}$$

The dry paint film thickness and actual coverage does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

Disclaimer

The information contained in this document is provided to the best of Nippon Paint's knowledge, based on laboratory testing and practical experience. As our products are considered semi-finished goods, their performance may be influenced by conditions beyond Nippon Paint's control. As such, we can only guarantee the quality of the product itself. Minor variations may be introduced to comply with local regulations. Nippon Paint reserves the right to modify the information in this document without prior notice.

Users are encouraged to consult Nippon Paint for specific guidance on the suitability of this product for their intended use and application method.

In case of discrepancies between language versions, the English (United Kingdom) version shall prevail.